

# Technical Data sheet

## Insert für MIGUTEC-Floor-Profiles FP 55, FN 50, FN 85, etc.

### 1. Product

- High quality Synca-Insert, hard wering, temperature resistant (-30°C up to +120°C)
- Good resistance to many chemicals (to be checked in detail)

### 2. Technical Data

Property	Unit	Test method	Measured values
Hardness	shore A	DIN 53505 / ISO 868	60
Density	g / cm <sup>3</sup>	DIN EN ISO 1183-1:2004	1,15
Tensile strength	N / mm <sup>2</sup>	DIN 53504 / ISO 37	9
Elongation	%	DIN 53504 / ISO 37	740
<b>Compression set</b>			
22 h / - 25 °C		ISO 815	80,00%
22 h / + 70 °C		ISO 815	45,00%
72 h / + 23 °C		ISO 815	12,00%

Remarks: The information provided in this document corresponds to our state of knowledge on the day of the publication. In case of new knowledge and experiences the present information can change. The technical data are based on measurements in random checks and show only one technical description of our products. They are not suited for specifications and are not confined from the check of the product for your purposes and procedures. Therefore MIGUA assumes no liability in connection with the use of this information.